

Waterproofing Slurry in Light Grey Colour

- in-depth waterproofing and protection
- permanent active
- approved for potable water contact
- light grey colour

PRODUCT DESCRIPTION

VANDEX CONCRETE GREY is a cementitious product providing in-depth waterproofing and protection of concrete structures, where a light grey colour similar to aged concrete is desired. VANDEX CONCRETE GREY is produced from Portland cement, specially treated quartz sand, and a compound of active chemicals. It is supplied in powder form in 25 kg bags and needs only to be mixed with water prior to application.

AREAS OF APPLICATION

VANDEX CONCRETE GREY can be applied to all structurally sound concrete – whether new or old. It is particularly recommended for use on exposed concrete structures.

Typical areas of application are:

- water reservoirs
- concrete walls above ground
- bridges
- underpasses
- dams, etc.

PROPERTIES

When VANDEX CONCRETE GREY is applied to a concrete surface, the active chemicals combine with the free lime and moisture present to form chemical complexes. These complexes block the capillaries and minor shrinkage cracks in the concrete to prevent any further water ingress (even under pressure). However, the Vandex will still allow the passage of water vapour through the structure (i. e. the concrete will still be able to "breathe").

VANDEX CONCRETE GREY is approved for use in contact with potable water. It is therefore suitable for the treatment of water storage tanks, reservoirs, water towers, etc.

SURFACE PREPARATION

All concrete to be treated with VANDEX CONCRETE GREY must be clean and have an open capillary system. Remove laitance, dirt, grease, etc. by means of high pressure water jetting or wet sandblasting. Faulty concrete such as cracks, honeycombing, etc. must be chased out, treated with Vandex and made good. Surfaces must be carefully pre-watered prior to the Vandex application. The concrete surface must be damp but not wet.

MIXING

VANDEX CONCRETE GREY is mechanically mixed with clean water to a consistency of thick oil paint. Approximate mixing ratio is 0.8 parts water to 2.0 parts powder (by volume).

Mix only as much material as can be used within 20 minutes and stir mixture frequently. If the mixture starts to set do not add more water, simply restir to restore workability.

APPLICATION

VANDEX CONCRETE GREY is normally applied in two coats by masonry brush or power spray. Apply the second coat whilst the first coat is still "green".

Post treatment

The treated areas should be kept damp for a period of five days and must be protected against direct sun, wind and frost, by covering with polythene sheeting, damp hessian or similar.

Note

Do not apply VANDEX CONCRETE GREY at temperatures below +5 °C. VANDEX CONCRETE GREY cannot be used as an additive to concrete or plasters.

CONSUMPTION

All surfaces to be treated should receive two coats of VANDEX CONCRETE GREY each coat 0.75 kg/m².

PACKAGING

25 kg PE-lined paper bag

STORAGE

When stored in a dry place in unopened, undamaged original packaging, shelf life is 12 months.

HEALTH AND SAFETY

VANDEX CONCRETE GREY contains cement. Irritating to skin. Risk of serious damage to eyes. – Keep out of reach of children. Do not breathe dust. Avoid contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. Wear suitable gloves and eye/face protection. – For further information please refer to Material Safety Data Sheet on www.vandex.com.

TECHNICAL DATA		
Aggregate state		powder
Colour		light grey
Bulk density	[kg/l]	approx. 1.3
Setting time	[min.]	90

All data are averages of several tests under laboratory conditions. In practice, climatic variations such as temperature, humidity, and porosity of substrate may affect these values.

The information contained herein is based on our long-term experience and the best of our knowledge. We can, however, make no guarantee since for a successful outcome, all circumstances in an individual case must be taken into consideration. Indications of quantities required are only averages which in certain cases might be greater.



CONCRETE PROTECTION AND WATERPROOFING

An **RPM** Company

**HEADOFFICE AND INTERNATIONAL SALES:
VANDEX INTERNATIONAL LTD**
P.O. Box, CH-4501 Solothurn/Switzerland
Phone: +41 32 626 36 36, Fax +41 32 626 36 37
E-mail: info@vandex.com www.vandex.com



**PRODUCTION AND SALES GERMANY/AUSTRIA:
VANDEX ISOLIERMITTEL-GESELLSCHAFT m.b.H.**
P.O. Box, 1406, D-21487 Schwarzenbek/Germany
Phone: +49 4151 89 15-0, Fax +49 4151 89 15 50
E-mail: info@vandex.de www.vandex.de