

Elastic adhesive and sealant

- 1 component
- adhesive for VANDEX FLEXTAPE
- can be applied on fresh concrete
- bonding to damp substrate
- resistant to frost during and after curing
- hand or spray application
- cures with humidity
- solvent free

PRODUCT DESCRIPTION

VANDEX UNIFLEX NV is a one-component adhesive and sealing compound based on silan modified polymers (SMP).

AREAS OF APPLICATION

VANDEX UNIFLEX NV is a universal adhesive and is used for bonding VANDEX FLEXTAPE over construction and movement joints as well as cracks in concrete structures. VANDEX UNIFLEX NV shows good adhesion to steel, aluminium, concrete, glass, wood, polyester, PVC, brick.

PROPERTIES

VANDEX UNIFLEX NV cures by reaction with humidity to an elastic sealant/adhesive. It bonds to damp substrates and has a high UV resistance. Workability at uneven substrates and over-head is guaranteed due to the paste-like consistency. The product is free of solvents, isocyanates and silicones. VANDEX UNIFLEX NV is resistant to frost. Temperatures below 0 °C prolongate the curing process in relation to the humidity.

SURFACE PREPARATION

The substrate must be clean and free from ice, grease, oil etc. The substrate may be slightly damp, but must not be saturated with water at the time of application. Useful substrate preparation is by water jetting 150 bar or grinding.

MIXING

Ready to use

APPLICATION

VANDEX UNIFLEX NV is applied by a standard air or hand operated gun. It is levelled to required thickness and width by a trowel or toothed comb.

Open packagings should be used as soon as possible.

On coated surfaces and other substrates not mentioned trials for adhesion and compatibility are recommended. The film formation and curing times depend on humidity and temperature. Curing time can be shortened by increasing humidity and temperature.

CONSUMPTION

Apply 1 mm of VANDEX UNIFLEX NV as adhesive for VANDEX FLEXTAPE. The edges of the applied VANDEX FLEXTAPE must be covered with VANDEX UNIFLEX NV.

200 ml VANDEX UNIFLEX NV per linear meter of VANDEX FLEXTAPE 150/1

300 ml VANDEX UNIFLEX NV per linear meter of VANDEX FLEXTAPE 200/1 or 200/2

PACKAGING

VANDEX UNIFLEX NV is supplied as ready-to-use 600 ml sausage (12 in a box)

STORAGE

When stored in a dry and cool place in unopened, undamaged original packaging, shelf life is 12 months.

HEALTH AND SAFETY

VANDEX UNIFLEX NV is not a dangerous substance. Wear suitable gloves and eye protection. Provide good ventilation if handling bigger quantities or in enclosed areas. In case of contact with eyes rinse immediately with plenty of water and seek medical advice.

For further information please refer to Material Safety Data Sheet on www.vandex.com.

TECHNICAL DATA		
Consistency		paste
Colour		grey
Odour		odourless
Density at 23 °C	[g/m ³]	approx. 1.4
Shore-A-hardness at 23 °C/50 rF		40 ± 2
Film formation at 23 °C/50 rF	[min]	< 30
Curing rate at 23 °C / 50% rh / 24 h	[mm]	2.5
Application temperature (substrate)	[°C]	>1 to +40
Temperature resistance (during curing)	[°C]	-10 to +40
Temperature resistance (hardened)	[°C]	-40 to +90
Chemical resistance		good resistance against oils and greases; limited resistance against fuel, esters, ketones and halogenated solvents; weather-proof
All data are averages of several tests under laboratory conditions. In practice, climatic variations such as temperature, humidity, and porosity of substrate may affect these values.		

The information contained herein is based on our long-term experience and the best of our knowledge. We can, however, make no guarantee since for a successful outcome, all circumstances in an individual case must be taken into consideration. Indications of quantities required are only averages which in certain cases might be greater.

Vandex[®]

CONCRETE PROTECTION AND WATERPROOFING

An **RPM** Company

**HEADOFFICE AND INTERNATIONAL SALES:
VANDEX INTERNATIONAL LTD**

P.O. Box, CH-4501 Solothurn/Switzerland
Phone: +41 32 626 36 36, Fax +41 32 626 36 37
E-mail: info@vandex.com www.vandex.com



**PRODUCTION AND SALES GERMANY/AUSTRIA:
VANDEX ISOLIERMITTEL-GESELLSCHAFT m.b.H.**

P.O. Box, 1406, D-21487 Schwarzenbek/Germany
Phone: +49 4151 89 15-0, Fax +49 4151 89 15 50
E-mail: info@vandex.de www.vandex.de