

Elasticized waterproofing slurry

- resistant to water aggressive for concrete
- suitable for areas of potential cracking
- applicable by mortar gun

Permeability to CO ₂	s _D > 50 m	 0761
Water vapour permeability	class II 5 m ≤ s _D ≤ 50 m	
Capillary water absorption	w < 0.1 kg/m ² · h ^{0.5}	Vandex Isoliermittel-GmbH Industriestr. 21 DE-21493 Schwarzenbek 09 267/150 EN 1504-2:2004/ZA.1d,1e Surface protection coating
Crack bridging ability	class A2 (20 °C)	
Adhesion strength	≥ 0.8 MPa	
Reaction to fire	class E	
Dangerous substances	complies with 5.3	

PRODUCT DESCRIPTION

VANDEX CEMELAST WHITE is a two component polymer modified, cementitious surface treatment.

VANDEX CEMELAST WHITE consists of VANDEX CEMELAST WHITE POWDER (dry component) and VANDEX CEMELAST LIQUID (polymer component).

AREAS OF APPLICATION

- substrates: concrete and masonry
- waterproofing and protection against water and moisture
- for cracks and areas of potential cracking
- foundations, slabs, retaining walls, structures, etc.

PROPERTIES

Owing to its composition of cement, quartz with well graded aggregate and selected additives, as well as the admixture of the polymer component, a waterproof and elastic coating is achieved. The initial and final bonding ability of VANDEX CEMELAST WHITE is excellent, making it suitable to be applied on horizontal as well as vertical surfaces. It is durable, resistant to frost and heat after setting and at the same time vapour permeable. It is an active barrier to carbon dioxide (CO₂) and resistant to water aggressive for concrete.

SURFACE PREPARATION

The substrate to be treated must be sound and even, open-pored, roughened and its surface free from voids, large cracks or ridges. Any adhesion reducing substances like bitumen, oil, grease, remains of paint or laitance have to be removed by suitable means.

Water leaks must be stopped e.g. with the VANDEX PLUG.

Thoroughly moisten the substrate, it must be damp but not wet at the time of application. Any surface water on horizontal surfaces must be removed.

Brick- and blockwork substrates

Any remaining plaster, render or other substances that could inhibit bonding must be removed back to the substrate. Gypsum, remains of wood or other foreign material must be removed by appropriate means. Loose pointing must be routed out and the substrate cleaned thoroughly.

MIXING

Before use, shake the container of the polymer component well.

Mix 25 kg of VANDEX CEMELAST WHITE POWDER with 9 kg of VANDEX CEMELAST LIQUID in a clean container for at least 3 minutes to a lump-free, homogeneous consistency. Use a high speed mechanical mixer.

Where site conditions require, rinse the container with clean water and add it to the mixture.

APPLICATION

VANDEX CEMELAST WHITE is applied with trowel or suitable spray equipment.

Depending on the slurry consistency a maximum of 4 kg/m² can be applied in one working cycle. In most cases the application of more than one coat is recommended; please refer to relevant specification.

If several coats are applied the previous coat must not be damaged during application of the following coat. The waiting time before applying the following coat depends on local climatic conditions such as humidity, temperature, etc. The previous coat is textured by suitable means whilst still plastic to form a key.

Trowel application

First a scratch coat is applied for maximum adhesion to the substrate, working from the bottom up. Ensure that all cavities in the substrate are filled in order to exclude any trapped air.

Spray application

VANDEX CEMELAST WHITE can be applied with a suitable fine mortar spraying device.

For maximum spray pattern it should be possible to adjust volume of product as well as air pressure and volume. The nozzle diameter is approx. 6 mm.

The first layer of Vandex is applied in circular motion with the spray nozzle held at a 90° angle to the substrate. The material is then flattened and keyed. The final layer can be left as a spray finish or treated to a specified finish.

Do not apply at temperatures below +5 °C, or to a frozen substrate.

CONSUMPTION

Type of water impact	Recommended overall application rate	Number of layers
Pressureless water	2.5-3.5 kg/m ²	1-2
Water under pressure	3.5-5.5 kg/m ² depending on water pressure	2-3

Note:

Substrate and application conditions have to be observed. Depending on surface roughness, consumption may vary.

CURING

Provide suitable protection against extreme weather conditions (e.g. rain, sun, wind, frost) while setting. The freshly treated surfaces should be protected from rain for a minimum period of 24 h.

The VANDEX CEMELAST WHITE coating must be fully cured before getting in contact with water. Avoid formation of water films or condensation on top of coating during 7 days after application.

Provide a relative humidity of 60-80% and good air exchange in enclosed areas.

PACKAGING

Dry component: 25 kg PE-lined paper bag

Polymer component: 9 kg PE-container

STORAGE

Dry component: When stored in a dry place in unopened, undamaged original packaging, shelf life is 12 months.

Polymer component: Store in a frost-free place. Shelf life in unopened, undamaged original packaging is 8 months.

HEALTH AND SAFETY

Please refer to the Safety Data Sheets VANDEX CEMELAST WHITE POWDER and VANDEX CEMELAST LIQUID on www.vandex.com.

TECHNICAL DATA		Dry component	Polymer component
Appearance		white powder	white liquid
		Wet mix	Hardened
Colour		white	white, marbled VANDEX CEMELAST WHITE is not a decorative coating.
Density of wet mix	[kg/l]	approx. 1.7	
Workability at 20 °C	[min.]	approx. 30	
Setting time at 20 °C	[h]		approx. 3-6
Elongation at 20 °C	[%]		approx. 13 ¹⁾
Tear resistance at 20 °C	[MPa]		approx. 0.9 ¹⁾
Crack bridging capacity at +20 °C	[mm]		≤ 0.4
Further data			refer to CE marking

All data is averages of several tests under laboratory conditions. In practice, climatic variations such as temperature, humidity, and porosity of substrate may affect these values.

The information contained herein is based on our long-term experience and the best of our knowledge. We can, however, make no guarantee since for a successful outcome, all circumstances in an individual case must be taken into consideration. Indications of quantities required are only averages which in certain cases might be greater.



RPM / Belgium N.V.
H.Dunantstraat 11B · B-8700 Tielt · T.:+32 (0) 51 40 38 01
Alteco Technik GmbH
Raiffeisenstraße 16 · D-27239 Twistringen · T.:+49 (0) 42 43 92 95 0

Vandex AG/ Vandex International Ltd
Rötistrasse 6 · CH-4500 Solothurn · T.:+41 (0) 32 626 36 46 / 36
Vandex Isoliermittel-Gesellschaft m.b.H.
Industriestraße 21 · D-21493 Schwarzenbek · T.:+49 (0) 41 51 89 15 0